

# Longitudinal Velocity of Sound

We measured during the years

in some Materials

MATERIAL	MIN	MAX
SPRUCE	4250	6300
PERNAMBUCO WOOD	4000	6150
ZAPATERO AMARANTO	4650	5480
SNAKE WOOD	4000	5300
GUAYACO	4500	5700
MAPLE (FLAMED)	3300	5200
BRASILWOOD	4200	4950
EBONY	3140	4000
ITALIAN BOXWOOD	3300	3900