


PERNAMBUCO



MATERIALS	Longitudinal Velocity	Density	Resonance Quality Q	Specific Elasticity	Young E × cm ²
PERNAMBUCO 1	6.070	0,90	67	368	331
PERNAMBUCO 2	5.145	1,25	41	264	331